



ExxonMobil™ LDPE LD 150 Series

Low Density Polyethylene Resin

Product Description

LD 150 series are LDPE grades, offering good blend mechanical properties and stiffness. Several additive packages are available according to the required surface properties.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe
Additive	<ul style="list-style-type: none"> LD 150BW: Antiblock: No; Slip: No; Thermal Stabilizer: Yes LD 150AC: Antiblock: 450 ppm; Slip: 500 ppm; Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Agricultural Film Blend Partner Co-Extrusion Films Collation Shrink Form Fill And Seal Packaging Freezer Film Lamination Film Medium Duty Shrink Film Shoppers
Form(s)	<ul style="list-style-type: none"> Pellets
Revision Date	<ul style="list-style-type: none"> March 2013

Resin Properties	Typical Value	Unit	Test Based On
Density	0.923	g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	0.75	g/10 min	ASTM D1238
Peak Melting Temperature	109	°C	ExxonMobil Method

Film Properties	Typical Value	Unit	Test Based On
Tensile Strength at Break MD	28	MPa	ASTM D882
Tensile Strength at Break TD	22	MPa	ASTM D882
Elongation at Break MD	310	%	ASTM D882
Elongation at Break TD	530	%	ASTM D882
Secant Modulus MD - 1% Secant	240	MPa	ASTM D882
Secant Modulus TD - 1% Secant	280	MPa	ASTM D882
Dart Drop Impact	190	g	ASTM D1709A
Elmendorf Tear Strength MD	350	g	ASTM D1922
Elmendorf Tear Strength TD	150	g	ASTM D1922

Optical Properties	Typical Value	Unit	Test Based On
Gloss (45°)	59		ASTM D2457
Haze	8.5	%	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

The test specimen were prepared on LD 150BW, 50µm (1.97mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio of 2.5 and temperature profile of 180 - 190°C (356 - 374°F).

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas

Asia Pacific

Europe, Middle East and Africa

ExxonMobil Chemical Company
13501 Katy Freeway
Houston, TX 77079-1398
USA
1-281-870-6050

ExxonMobil Chemical Asia Pacific
1 HarbourFront Place
#06-00 HarbourFront Tower One
Singapore 098633
+66-2-1638699

ExxonMobil Chemical Europe
Hermeslaan 2
1831 Machelen, Belgium
420-239-016-274

Typical properties: these are not to be construed as specifications.

©2013 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[Download datasheets at www.exxonmobilpe.com](http://www.exxonmobilpe.com)